



## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

#### CHARACTERISTICS

With the UVALUX<sup>®</sup> U0832 Coldfoil Adhesive we present a UV curing adhesive, especially for printing of labels and packaging in offset- or letterpress printing. UVALUX<sup>®</sup> U0832 is grey dyed and has an increased viscosity for printing on strong absorbent substrates.

#### TECHNICAL DATA

Drying/Curing	UV-Hg (Mercury Vapour)
---------------	------------------------

Substrate	Paper Uncoated - Paper Coated
-----------	-------------------------------

Printing Process	Offset Sheet-Fed - Offset Web-Fed - Letterpress
------------------	-------------------------------------------------

Press Performance	Sharply Printed Edges - Good Ink-Water-Balance - High Reactivity
-------------------	------------------------------------------------------------------

Surface Properties	Adhesion Optimized - Tinted
--------------------	-----------------------------

Application	Folded Box - Flexible Packaging - Self Adhesive Labels
-------------	--------------------------------------------------------

End Application	Non-Food
-----------------	----------

Market	Labels - Packaging
--------	--------------------

#### PACKING UNITS

- + 1 kg plastic can (black)
- + 2,5 kg plastic can (black)

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

#### TECHNICAL SERVICE CENTER

Kindly note that we are ready at any time for competent technical application support on your site. Please contact our technical service centre for printing inks:

Ink-Service@Zeller-Gmelin.de  
Tel: +49 7161 802-279

#### ADDITIVES

##### W963 UV Wash Up with Lemon Smell

Suitable for cleaning inking systems, sleeves, plates, blankets, etc.

Not approved for automatic washing units.

Before starting printing, the washing agent must be completely dried off, otherwise the printing behaviour may be impaired.

##### Remark:

The addition of any additive might change the overall characteristics of the printing ink.

#### STORAGE

##### Optimal storage conditions:

The optimal storage temperature is 20°C. Higher storage temperatures reduce the shelf-life.

##### Remarks:

- protect from frost
- store in a cool and dark place
- stir or shake well before use
- can should be closed immediately after usage

##### Warranty:

If the products are stored properly, we warranty the product performance for a shelf life of 12 months from the date of delivery. Deviating from this, we warranty only 6 months product performance for all deliveries in large containers over 10kg filling quantity.

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

#### PRACTICE REMARKS

##### Printing Materials

We recommend using ester and ketone resistant rollers (EPDM-material). The inking roller, rubber blanket and printing plate have to be resistant against UV-inks and UV-detergents (see manufacturers instructions).

##### Process description coldfoiling

Cold foiling is procedure where a foil is transferred to a substrate by means of a special adhesive. A UV-curing adhesive is printed using a regular printing unit. Then the foil is laminated onto the substrate. The foil image remains only where the adhesive has been printed. Excess foil is stripped off with the carrier material. The foil must be suitable for the application, so the adhesive can be cured through the foil (UV transmissible). Suitable printing inks for overprinting the applied foil: UVALUX<sup>®</sup> U70

##### Adhesive lay-down

If too much glue is applied it could be squeezed outside the image area during lamination with the foil. This would result in poor print definition and edges which are not sharp. In extreme cases even the carrier film can be torn apart. Insufficient glue application would lead to poor removal of the metallised layer from the carrier film resulting in a patchy print.

Running the adhesive on a cold machine can lead to sensitive troubles because of the adhesive's high tack. Therefore make sure to apply the adhesive always on an operationally warm machine.

##### Control of the adhesive

The adhesive is dyed, facilitating the control of even film weights by visual examination or more accurately using a densitometer.

Examples for density values: 0,35-0,40 measured with black filter

The indicated values refer to prints on standard coated paper „Norm Kunstdruckpapier Apco 2/2“ and shall only give a reference value. The type of substrate has a significant influence on the density values. Therefore other printing materials may show considerably different density readings.

##### Foil Characteristics

Foils with easy release from the carrier film enable optimum transfer, especially with high press speeds. They are ideal for use on full coverage designs. Foils with lower release properties from the carrier film (more firmly attached, harder to remove) enable sharper foiling, especially with fine lines and halftone work. However there is an increased risk of incomplete foil transfer.

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

#### Fountain Solution

Approved fountain solution parameters:

a) ph-value: 4,8 - 5,2

b) Water hardness: 9 - 12° dH

We recommend the use of temperature controlled ink ducts and fountain solution.

#### Preliminary Tests Recommended

Before beginning to print we recommend practice oriented pretests on your substrate, in order to test the desired characteristics of the finished product.

#### MARKING

##### Marking according to EC legislation:

Our inks are classified and marked according to EC legislation and the German "Gefahrstoffverordnung" (German dangerous substances regulation).

The material safety data sheet (MSDS) is available on request.

#### MISCELLANEOUS

##### Available Variants

UVALUX<sup>®</sup> U0830: Yellow dyed, for the EU market

UVALUX<sup>®</sup> U0831: Grey dyed, for the EU market

UVALUX<sup>®</sup> U0832: Grey dyed, increased viscosity, for the EU market

UVALUX<sup>®</sup> U0833: Grey dyed, increased viscosity, for the US market (TSCA conform)

#### REMARKS ON MIGRATION AND CONFORMITY

The following remarks are valid for the production of food packaging which complies with the regulations in the European Union. We are not able to provide statements concerning food packaging legislation of countries outside the EU.

Regulation (EC) No 1935/2004 requires that the person responsible for "placing on the market" of a packaging article must have an appropriate documentation available to demonstrate the compliance with the rules related to food processing and distribution.

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

Not only the used materials influence food-legislation related properties of a packaging. The production process of the packaging has a significant impact as well.

Therefore, we recommend our customers to send their finished products to a recognized analytical institute for examination and certification. That way compliance with legal requirements can be proven.

The transfer of substances from the packing into the filling is called migration. The following production parameters have a significant influence on the degree of migration:

- correct processing, especially the complete through-cure of the ink film
- type of substrate and substrate thickness (sufficient barrier properties of the substrate)
- prevention of a direct contact of the printing ink with the food
- selection of printing inks which are suitable for FCM applications

The UVALUX<sup>®</sup> U0832 Coldfoil Adhesive has no special FCM formulation. Therefore we recommend for food packaging FCM ink series and lacquers which are available for many applications.

You should ensure by migration analysis that no migration through the entire packaging material takes place. Due to the multitude of packaging materials and their different barrier properties we are not able to provide a general statement regarding through-migration.

Please note that migration can also occur by set-off when the printed surface is pressed against the food-contact surface of the packaging in the stack or reel.

#### DECLARATION OF COMPOSITION AND PRODUCT DECLARATION

As there are no specific regulations concerning printing inks and varnishes Zeller+Gmelin -like other ink suppliers- is obliged to follow regulations in the EU not directly related to printing inks.

#### Regulation (EC) No 1935/2004

Article 3 of the Regulation (EC) No 1935/2004 (impact on food) demands, that materials and articles do not transfer their constituents to food in quantities which could endanger human health or bring about an unacceptable change in the composition of the food or bring about a deterioration in the organoleptic characteristics thereof.

We urgently advise you to use for printing on food packaging only printing inks/lacquers which we specifically

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX® U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

recommend for this application based on FCM formulations.

A possible impact on the quality of food does not solely depend on the printing ink/lacquer itself but is depending on the complete production chain (ink laydown, UV-power, substrate, etc.). For this reason we are not able to confirm a general compliance to Regulation (EC) No 1935/2004 only based on the composition of the ink/lacquer.

Based on Article 17 (traceability) material and articles shall be ensured at all stages in order to facilitate control, the recall of defective products, consumer information and the attribution of responsibility.

All raw materials for ink/lacquer batches at Zeller+Gmelin are documented in writing on the Formula Component Report. Based on the batch number every raw material can be clearly traced back to the raw material batch.

#### Regulation (EC) No 2023/2006

This so called GMP regulation (Good Manufacturing Practice) defines the requirements on the different participants in the manufacturing process of materials and articles intended to come into contact with food. It requests a system for quality assurance, control and documentation (§5-7). The EuPIA defined the requirements on printing ink manufacturers in the EuPIA-GMP.

#### Regulation (EU) No 10/2011 and amendments

Regulation (EU) No 10/2011 establishes the specific rules for plastic materials and articles to be applied for their safe use and repeals Commission Directive 2002/72/EC of 6 August 2002 on plastic materials and articles intended to come into contact with foodstuff.

In this regulation, the so called PIM (Plastic Implementation Measure) limits are set for substances, which are allowed to be in direct contact with food and are allowed to migrate into food up to the level listed in Annex I. Substances used in printing inks must not (with few exemptions) get in direct contact with food and are therefore not listed in Annex I.

Paragraph (30) states, that coatings, printing inks and adhesives are not yet covered by a specific EU legislation and therefore not subject to the requirement of a declaration of compliance.

For the migration of non-authorized substances through a functional barrier into food a limit of 0,01 mg/kg (10 ppb) is defined.

Substances that are mutagenic, carcinogenic or toxic to reproduction should not be used without previous authorisation in food contact materials or articles and should therefore not be covered by the functional barrier concept.

#### CEPE / EuPIA – Exclusion Policy

CEPE is the European Council of producers and importers of paints, printing inks and artists colours whereas EuPIA is the European Printing Ink Group of CEPE. Many years ago the printing ink industry has

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.



## TECHNICAL DATA SHEET

### UVALUX® U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

implemented voluntarily the Exclusion Policy for specific substances.

Zeller+Gmelin is an active member in EuPIA and subgroups. The raw materials used by Zeller+Gmelin for the formulation of our printing inks/lacquers meet the guidelines of the CEPE / EuPIA Exclusion Policy. Thus CMR 1A and 1B raw materials (cancerogenic, mutagenic and reprotoxic) are not used in our printing inks /lacquers.

#### Heavy Metals

We herewith confirm that the limits of the heavy metals lead, cadmium, mercury and chromium(VI) layed down by the European packaging and packaging waste directive 94/62/EC as well as the „Model Toxics in Packaging Legislation“ of TPC (former CONEG) are met. The limits layed down in EN 71-3 („ safety requirements for toys“) are also met. Heavy metals are not part of our formulations.

#### Hazardous substances

Substances mentioned in the Directive 2002/95/EC (RoHS) and Directive 2011/65/EC are not intentionally used in our printing inks/lacquers.

SVHC-substances (substances of very high concern): In our products no substances are used which are classified as CMR 1A & 1B, PBT (PBT pollutants are chemicals that are toxic, persist in the environment and bioaccumulate in food chains), vPvB (Substances that are potentially very persistent and very bioaccumulative) und endocrine disruptors (artificial hormones).

Furthermore we confirm that our printing inks/lacquers are in accordance with the Regulation (EC) No 1895 /2005 (repeals the Directive 2002/16/EC).

#### DIN EN ISO certification

The production site of Zeller+Gmelin / Germany is certified according to DIN EN ISO 9001:2015 and DIN EN ISO 14001:2015.

#### Swiss Ordinance 817.023.21

This ordinance regulates materials and articles intended to come into contact with food. On 01.04.2008 the ordinance was changed to include regulations concerning printing inks. Since 01.04.2010 only packaging which has been produced with printing inks based on listed raw materials may be supplied to consumers. We urgently recommend to only use our FCM products for food packaging being subject to SO817.023.21.

#### Please note:

According to applicable law the manufacturer of the finished article and the filler have the full legal responsibility to ensure that their product is fit for its intended purpose and complies with the applicable rules (not the supplier).

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.





## TECHNICAL DATA SHEET

### UVALUX<sup>®</sup> U0832 Coldfoil Adhesive

Coldfoil Adhesive for UV Offset and UV Letterpress, grey tinted, increased viscosity

Please also consider the relevant publications of the European Printing Inks Association EuPIA (<http://www.eupia.org>).

There are many types of final packaging and the printing ink/lacquer is only one constituent. Since the parameters in the printing, packing and storage processes are not under the control of the printing ink manufacturer, the printing ink suppliers are not able to issue certificates or declarations of compliance which cover the legal responsibility of the entire packaging chain.

The statements made in this declaration are according to our current knowledge. They do not absolve the user from its own responsibility to ascertain that our products are suitable for his application.

UVALUX U0832 Kaltfolienkleber

10/2022-UVALUX U0832 Kaltfolienkleber-10

This information corresponds to our current knowledge. They do not exempt the processor from carrying out its own tests. A legally binding assurance of certain properties or a suitability for a specific application cannot be derived from our information. Any existing legal provisions and regulations concerning the handling and use of the products must be observed by the recipient of our products himself. We would also like to point out that the specifications of our product always take precedence over objective quality requirements.